

Peelable

19 PPH / PPHA

Data Sheet (January 2018)

Product family Introduction

Nuroll Peelable film is a bi-axially oriented polyester (BOPET) film with an amorphous polyester heat seal layer. It is specially designed for heat sealable lidding application on packaging refrigerated and frozen foods.

Nuroll Peelable film shows also an excellent hot-tack for hot filling process. It can be placed at temperature down to -60°C and up to 200°C , and it is designed for self opening during cooking, when temperature goes over 90°C .



Nuroll Peelable film is dual ovenable, pasteurizable and provides strong, consistent peeling to substrates such as APET, CPET, PETG and PVC in all the usual conditions.

The heat seal layer is available in 2 different thicknesses, $2\mu\text{m}$ (**PPL** grade) and $3,5\mu\text{m}$ (**PPH** grade).

Nuroll Peelable is commercially available also with **anti-fogging** characteristics to assure more clarity and transparency when stored in refrigerators.

Sealing properties

Nuroll Peelable film shows a very good seal immediately after the sealing (hot tack properties), for this reason it represents the right choice for hot filling and MAP packaging applications. Its particular formulation guarantees a good seal without stress the shredding behavior.



Welding force of 23 PPH on different substrates

Welding conditions	Film/Film	Film/Film at 0°C	Film/ CPET (APET layer)	Film/ Cardboard	Film/ Cardboard at 0°C	Film/ 23μ Film plain
140°C-4bar-1sec	> 6,5	5	5,5	2,5	2,5	2,5
140°C-4bar-2sec	> 6,5	5,5	6,5	3,5	2,5	2,5
140°C-4bar-4sec	> 6,5	5,5	7,5	3,5	2,5	2,5
160°C-4bar-1sec	> 7	6,5	7	3	3	3
160°C-4bar-2sec	> 7	6,5	7,5	3	3	3
160°C-4bar-4sec	> 7	6,5	7,5	4	3	3
190°C-4bar-1sec	> 7	> 7	7	3,5	3,5	4
190°C-4bar-2sec	> 7	> 7	8	4	3,5	4
190°C-4bar-4sec	> 7	> 7	8	4	3,5	4

Specimen structure	N/15 mm
Film/Film	> 6,5
Film/ 50μ Film plain	5
Film/ Cardboard	3,5
Film/ APET	7,5
Film/ 100% CPET	5

FORCE is measured by INSTRON dynamometer in N Sample dimension is 15 mm width

Cardboard is laminated with BOPET film, cardboard polyester extrusion coated behavior is like CPET

Peelable


19 PPH / PPHA

Product description

Nuroll PPH is suggested when strong sealability is requested, when tray design is complex or the filling process can dirt the sealing area (by powder, fats or liquids).

Nuroll PPH is commercially available in nominal thicknesses (plain film) of 23, 36 microns. For different thicknesses it is necessary to agree a minimum order and to full chart the mother roll width.

Nuroll PPH is commercially available also with anti-fogging characteristics (**PPHA**) to assure more clarity and transparency when stored in refrigerators



Main Applications

Food containing fats, liquids, powder; food packaging for pasteurization; food packaging for hot fill process; food packaging for MAP process

Technical details

Nuroll PPH is usually supplied with following characteristics:

- ⊕ **Core diameter:** 6 inches (152.76 mm)
- ⊕ **Film width:** min 400 mm, max 1400mm
- ⊕ **Film length:** According with film thickness and max external reel diameter 640mm

Film Thickness (microns)	19
Standard reel length (m)	10.000

- ⊕ **Packing presentation:** suspended reel; wooden endboards, lid and pallet; stretchable PE film

Different characteristics than the above on request

Storage conditions

Nuroll PPH need to be stocked in a close warehouse and preserved from the light and from the humidity.

Reels must be not stacked

Nuroll will not accept any responsibility for material older than 1 year from the delivering

Compliance with regulations

Polyester Film produced by Nuroll SpA, complies with EEC, Italian and FDA requirements on packaging for direct contact with foodstuffs

Peelable

19 PPH / PPHA

Properties	Unit	Test Method	Typical values PPH grade	Typical values PPHA grade	
Base film thickness	Microns	ASTM E 252	19	19	
Coating thickness	Microns	ASTM E 252	3,5	3,5	
Total thickness	Microns	ASTM E 252	22,5	22,5	
Yield (nominal)	m ² /kg	ASTM E 252	33,3	33,3	
	g/m ²		30	30	
Tensile strength	MD	ASTM D 882	N/mm ²	230	230
	TD		kg/inch	11,1	11,1
	MD		N/mm ²	240	240
	TD		kg/inch	12,1	12,1
Elongation at Break	MD	ASTM D 882	%	130	130
	TD		%	120	120
Thermal Shrinkage 150 °C-30'	MD	ASTM 1204	%	1,5	1,5
	TD		%	0,5	0,5
Haze	%	ASTM D1003	8	10	
MVTR (38 °C, 90%RH)	g/m ² *day	ASTM E398	30	30	
OTR (20 °C, 0%RH)	cc/m ² *day	ASTM D3985	70	70	
Welding force (on itself) 140 °C; 4 bar; 4 s	N/15mm	Internal	6,5	6	

⇒ For thicknesses different than those reported above it is necessary to agree a minimum order and to full chart the mother roll width

1. This information is the best currently available on product and it is subject to revision as additional knowledge and experience is gained.
2. The results obtained and the above properties refer to average value of laboratory tests. Therefore, such results have only to be considered as an indicative general guide to material properties and not as an implied guarantee that the product actually has said properties and/or a warranty of fitness for a particular purposes and/or suggestion for infringement of any existing patents.
3. Due to many factors which may affect customer production process, including but not limited by different equipments and techniques used, PPH-PPHA film must be qualified before being used in any application.